

OCEANZ PA11

Datasheet for polyamide parts produced by Selective Laser Sintering



PA11 is a bio-based whitish polyamide material. Compared to PA12 it offers a higher elongation at break, elasticity and impact resistance. Typical applications are therefore environments where high deformations occur. In addition, the material does not splinter when fractured.

Laser-sintered parts made from Oceanz PA11 possess excellent material properties:

- high elongation and impact resistance
- bio compatible according to EN ISO 10993-1

Typical applications of the material are fully functional plastic parts of highest quality. Due to the excellent mechanical properties the material is often used to substitute typical injection moulding plastics. The biocompatibility in combination with the high elasticity and impact strength allows its use for prosthetic and orthotic devices.

Oceanz PA11 which is processed in our ISO9001 can be polished, coloured and coated. Oceanz PA11 is also available as medical grade (ISO13485). Products processed in ISO13485 cannot be polished, coloured and coated.

Part properties	Value	Unit
Part colour	Whitish	-
Part density	0.95	g/cm³
Minimum wall thickness	1.0	mm
Layer thickness	0.10 - 0.12	mm
Max. product size	335 x 335 x 603	mm
Tensile modulus XY / Z	1700 / 1800	MPa
Tensile strength XY / Z	45 / 38	MPa
Strain at break XY / Z	28 / 14	%
Charpy Impact strength (notched)	5.1 / 3.9	kJ/m²
Izod Impact strength (notched)	6.5 / 4.8	kJ/m²
Melting temperature	200	°C

Please note that all mentioned mechanical properties are optimum values according to manufacturer. Due to the layer by layer production process and the specific design of each individual product values may

All information in this data sheet is based on appropriate testing further details of Visit Oceanz which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. The data are subject to change without notice as part of our continuous development and improvement processes.

The content of this material datasheet may be subject to copyright restrictions. Quoted results are compiled from Oceanz test data, suppliers source data, and may contain data values from other material specific sources.

Maxwellstraat 21, 6716 BX EDE T: +31 (0) 318 769 077 M: info@oceanz.eu W: www.oceanz.eu



differ. If specific properties and/or dimensions are critical, always contact us so we can inform you how to obtain required specifications!