


## Design guidelines


For parts produced in PA12 based materials with Selective Laser Sintering

### DESIGN FEATURES

	Maximum part dimensions	Walls		
		Minimum thickness [mm]*	Optimum thickness [mm]	Maximum thickness [mm]
	100 x 100 x 100 mm	0.7	1.5-6.0	8.0
	250 x 250 x 250 mm	1.0	2.0-8.0	10.0


Recommended wall thickness

\* polishing not possible


	Maximum part dimensions	Holes		
		Minimum diameter [mm]	Optimum diameter [mm]	Accuracy* diameter [mm]
	100 x 100 x 100 mm	1.5	≥ 2.0	+ 0.10 - 0.30
	250 x 250 x 250 mm	2.0	≥ 3.0	+ 0.10 - 0.30

Recommended hole diameter


\*valid for nominal sizes between 4 and 50 mm

	Maximum part dimensions	Feature size		
		Minimum width [mm]	Optimum width [mm]	Maximum width [mm]
	100 x 100 x 100 mm	1.5	≥ 2.0	n/a
	250 x 250 x 250 mm	2.0	≥ 3.0	n/a

The recommended width of a feature to ensure it will not fail to print<sup>1</sup>

	Maximum part dimensions	Channels		
		Minimum diameter [mm]	Optimum diameter [mm]	Maximum diameter [mm]
	100 x 100 x 100 mm	2.5	≥ 4.0	n/a
	250 x 250 x 250 mm	3.0	≥ 5.0	n/a


The recommended channel diameter<sup>2</sup>

	Maximum part dimensions	Connecting parts: Moving		
		Minimum* clearance [mm]	Optimum** clearance [mm]	Maximum clearance [mm]
	100 x 100 x 100 mm	0.3	0.5-0.6	n/a
	250 x 250 x 250 mm	0.5	0.6-0.8	n/a


The recommended clearance between two moving parts


\* printed separately

\*\* printed as one

	Maximum part dimensions	Connecting parts: Press fit
		Minimum clearance [mm]
	100 x 100 x 100 mm	0.1
	250 x 250 x 250 mm	0.2


The recommended clearance between two parts to obtain press fit

<b>Embossed or engraved details or text</b>				
<i>The recommended dimensions for features raised or recessed below the model surface</i>				
	<b>Maximum part dimensions</b>	<b>Minimum feature width/height [mm]</b>	<b>Optimum feature width/height [mm]</b>	<b>Minimum font height [mm]</b>
	100 x 100 x 100 mm	0.5	1.0	5.0
	250 x 250 x 250 mm	0.5	1.0	5.0


<b>Escape holes</b>			
<i>The recommended hole diameter to ensure powder free hollow parts</i>			
	<b>Maximum part dimensions</b>	<b>Minimum diameter [mm]</b>	<b>Minimum amount of escape holes</b>
	100 x 100 x 100 mm	8.0	2
	250 x 250 x 250 mm	8.0	2

- 1 - Maximum feature height to width ratio of 5:1
- 2 - Maximum channel length = 100 mm

## PART QUALITY

<b>Tolerances*</b>			
<i>Valid for nominal sizes above 10 mm</i>			
	<b>Max. part dimensions</b>	<b>Linear dimensions [mm]</b>	<b>Dimensions Z [mm]</b>
	100 x 100 x 100 mm	IT12 [ISO 286-1] or $\pm 0.3\%$ of the longest diagonal	+ 0.5% - 0.3%
	250 x 250 x 250 mm	IT12 [ISO 286-1] or $\pm 0.4\%$ of the longest diagonal	+ 0.6% - 0.3%

\* with a minimum of  $\pm 0.30$  mm

<b>Required data format</b>			
<i>Oceanz printing technology uses .STL format, all files are converted to this format</i>			
	<b>STL conversion</b>	<b>Surface deviation [mm]</b>	<b>Angle tolerance [°]</b>
	Export settings	0.01	10-20

This guide covers specific details and design rules how to avoid unintended failures when designing for SLS. To avoid print failure, values for each specification must stay within the minimum-maximum range. To guarantee our manufacturing tolerances, your design should meet the optimum values for each specification. Please note that due to the layer by layer production process and the specific design of each individual product values may differ.

***If your design contains specific details or features not mentioned in our design rules, or your design exceeds the maximum part dimensions, please contact us, so we can advise you how to obtain required part quality.***

All information in this datasheet is based on appropriate testing further details of which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. The data are subject to change without notice as part of our continuous development and improvement processes.

The content of this datasheet may be subject to copyright restrictions. Quoted results are compiled from Oceanz test data.

### Visit Oceanz

Maxwellstraat 21, 6716 BX EDE  
 T: +31 (0) 318 769 077  
 M: [info@oceanz.eu](mailto:info@oceanz.eu)  
 W: [www.oceanz.eu](http://www.oceanz.eu)

Revision date: 01/05/2022

# Tolerance grades

ISO 286-1:2010



Table 1 – Values of standard tolerance grades for nominal sizes up to 800 mm, extracted from ISO standard ISO 286-1:2010.

Nominal size (mm)		IT12 <sup>[1][3]</sup> Standard tolerance values [mm]	IT13 <sup>[1][3]</sup> Standard tolerance values [mm]
Above	Up to and including		
-	3	n/a	n/a
3	6	0.12 <sup>[2]</sup>	0.18 <sup>[2]</sup>
6	10	0.15 <sup>[2]</sup>	0.22 <sup>[2]</sup>
10	18	0.18	0.27
18	30	0.21	0.33
30	50	0.25	0.39
50	80	0.30	0.46
80	120	0.35	0.54
120	180	0.40	0.63
180	250	0.46	0.72
250	315	0.52	0.81
315	400	0.57	0.89
400	500	0.63	0.97
500	630	0.70	1.10
630	800	0.80	1.25

[1] To guarantee IT12 tolerances values, your design should meet the optimum values of the Oceanz design guidelines. For parts that do not meet these values or are larger than 250x250x250 mm IT13 tolerance values can be expected.

[2] For nominal values between 3 and 10 mm, tolerance values of line 10-18 mm are valid

[3] Tolerance values in z-direction may slightly differ due to z-growth (technology dependent)

This classification can be compared with ISO 2768-1:1990 for linear dimensions. For parts up to 250x250x250 mm classification 'm' will be valid for linear dimensions of 6 mm and larger. For bigger parts tolerance class 'c' will apply.

All information in this datasheet is based on appropriate testing further details of which are available on request and is stated to the best of our knowledge and belief at the time of publication. It is presented apart from contractual obligations and does not constitute any guarantee or warranty express or implied of properties or of process or application possibilities in individual cases. The data are subject to change without notice as part of our continuous development and improvement processes.

The content of this datasheet may be subject to copyright restrictions. Quoted results are compiled from Oceanz test data.

## Visit Oceanz

Maxwellstraat 21, 6716 BX EDE  
T: +31 (0) 318 769 077  
M: [info@oceanz.eu](mailto:info@oceanz.eu)  
W: [www.oceanz.eu](http://www.oceanz.eu)

Revision date: 01/05/2022